

# Dynafoam 30% Reduction

Thermoset, Unspecified

Saint Gobain - Norton

## Message:

Dynafoam 30% Reduction is a Thermoset, Unspecified (TS, Unspecified) product. It can be processed by foam processing and is available in North America. Applications of Dynafoam 30% Reduction include foam and sealing applications.

Characteristics include:

Heat Resistant

Chemical Resistant

General Information			
Features	Fast Cure		
	Foamable		
	Good Chemical Resistance		
	Good Heat Aging Resistance		
	High Heat Resistance		
Uses	Foam		
	Seals		
Appearance	Black		
	Colors Available		
Forms	Pellets		
Processing Method	Foam Processing		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm <sup>3</sup>	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Elongation (Yield)	380	%	ASTM D638
Compressive Strength	0.0621	MPa	ASTM D695
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	141	°C	ASTM D794
Brittleness Temperature	-40.0	°C	ASTM D746
Thermoset	Nominal Value	Unit	
Post Cure Time (22°C)	0.25 to 24	hr	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

