

# LubriOne™ ATT-000/5T Black

Acetal (POM) Copolymer

PolyOne Corporation

## Message:

LubriOne™ Lubricated and Wear-Resistant Compounds have been specifically formulated to be self-lubricating materials, offering low coefficient of friction and improved wear resistance properties. LubriOne compounds have been demonstrated to reduce friction, noise, vibration, heat buildup and improve product durability.

General Information			
Features	Copolymer		
	Good Wear Resistance		
	Low Friction		
	Lubricated		
Uses	Appliance Components		
	Automotive Applications		
	Bearings		
	Business Equipment		
	Consumer Applications		
	Conveyor Parts		
	Gears		
	Industrial Applications		
	Printer Parts		
	Pulleys		
	Rollers		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	1.5 to 2.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>1</sup>	965	MPa	ASTM D638
Tensile Strength <sup>2</sup> (Yield)	33.8	MPa	ASTM D638
Tensile Elongation <sup>3</sup> (Break)	40	%	ASTM D638
Flexural Modulus	1080	MPa	ASTM D790
Flexural Strength (Yield)	41.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	80	J/m	ASTM D256A
Injection	Nominal Value	Unit	

Drying Temperature	71.1	°C
Processing (Melt) Temp	188 to 210	°C
Mold Temperature	71.1 to 82.2	°C
NOTE		
1.	Type I, 5.1 mm/min	
2.	Type I, 5.1 mm/min	
3.	Type I, 5.1 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

