

# ELASTOSIL® R 420/30

Silicone

Wacker Chemie AG

## Message:

Silicone Rubber, HTV  
Extrudates, food contact, Plastics and Rubber Processing  
Extrudates, Technical, Plastics and Rubber Processing  
Extruded parts; tap water and wastewater contact, Plastics and Rubber Processing  
Molded Parts, Food Contact, Plastics and Rubber Processing  
Molded Parts, Technical, Plastics and Rubber Processing  
Molded parts; tap water and wastewater contact, Plastics and Rubber Processing

General Information			
Features	Food Contact Acceptable		
	Good Abrasion Resistance		
	Good Tear Strength		
Uses	Automotive Applications		
	Compounding		
	Gaskets		
	Membranes		
	Potable Water Applications		
	Profiles		
	Seals		
	Valves/Valve Parts		
Processing Method	Compression Molding		
	Extrusion		
	Press Molding		
	Profile Extrusion		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density	1.10	g/cm <sup>3</sup>	ISO 1183
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	31		DIN 53505
Tensile Strength	8.00	MPa	DIN 53504
Tensile Elongation at Break	670	%	DIN 53504
Compression Set	28	%	DIN ISO 815-B
Tear Strength	26.0	kN/m	ASTM D624B
Rebound Resilience	53	%	DIN 53512

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

