

# SEETEC LLDPE UL911A

Linear Low Density Polyethylene  
Lotte Chemical Corporation

Message:

UL911A is manufactured by Unipol process technology.  
UL911A is a melt blend grade of LDPE and LLDPE designed for blown film applications.  
UL911A has good mechanical properties, excellent optical properties and good processability.

General Information			
Additive	Antiblock		
	Antioxidant		
	Slip		
Features	Antiblocking		
	Antioxidant		
	General Purpose		
	Good Processability		
	Opticals		
	Slip		
Uses	Film		
	General Purpose		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.2	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	40	μm	ASTM D882
Tensile Strength			
MD : Break, 40 μm,Blown Film	37.8	MPa	
TD : Break, 40 μm,Blown Film	35.3	MPa	ASTM D882
Tensile Elongation			
MD : Break, 40 μm,Blown Film	680	%	
TD : Break, 40 μm,Blown Film	700	%	
Dart Drop Impact (40 μm, Blown Film)	100	g	ASTM D1709
Elmendorf Tear Strength <sup>1</sup>			ASTM D1922
MD : 40.0 μm	34.3	kN/m	
TD : 40.0 μm	78.5	kN/m	
Optical	Nominal Value	Unit	Test Method

Gloss (45°, 40.0 µm, Blown Film)	82		ASTM D2457
Haze (40.0 µm, Blown Film)	5.5	%	ASTM D1003
NOTE			
1.	Blown Film		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT