

Indothene LL 20FS020

Linear Low Density Polyethylene

Reliance Industries Limited

Message:

Indothene LL 20FS020 is a Linear Low Density Polyethylene product. It is available in Africa & Middle East or Asia Pacific. Typical application: Film.

| General Information | | | |
|---|---------------|-------------------|-------------|
| Uses | Film | | |
| Forms | Granules | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.920 | g/cm ³ | ASTM D1505 |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 kg) | 2.0 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Coefficient of Friction | 0.15 | | ASTM D1894 |
| Films | Nominal Value | Unit | Test Method |
| Tensile Strength | | | ASTM D882 |
| MD : Break | 29.4 | MPa | |
| TD : Break | 24.5 | MPa | |
| Tensile Elongation | | | ASTM D882 |
| MD : Break | 800 | % | |
| TD : Break | 950 | % | |
| Dart Drop Impact | 90 | g | ASTM D1709 |
| Elmendorf Tear Strength | | | ASTM D1922 |
| MD | 200 | g | |
| TD | 400 | g | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT