

G-PAEK™ 1100G

Polyether Ketone

Gharda Chemicals Ltd.

Message:

Product Details: Ultra high Performance thermoplastic polymer, virgin, semicrystalline granules suitable for Injection Molding, easy flow, Beige in color.

Application Areas: Suitable for high temperature application, high wear & abrasion resistance, high chemical resistance is required & for metal replacement with plastics etc.

General Information			
Features	Good Abrasion Resistance		
	Good Chemical Resistance		
	Good Flow		
	Good Wear Resistance		
	High Heat Resistance		
	Semi Crystalline		
Uses	High Temperature Applications		
	Metal Replacement		
Appearance	Beige		
Forms	Granules		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	
Spiral Flow ¹	33.7	cm	ASTM D3123
Molding Shrinkage ²			
Flow	1.1	%	
Across Flow	1.3	%	
Water Absorption (Equilibrium)	0.060	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	98		ASTM D785
Durometer Hardness (Shore D)	87		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	4200	MPa	ASTM D638
Tensile Strength (Yield, 23°C)	110	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	20 to 25	%	ASTM D638
Flexural Modulus (23°C)	4100	MPa	ASTM D790
Flexural Strength (23°C)	185	MPa	ASTM D790
Compressive Strength	135	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	60	J/m	ASTM D256

Unnotched Izod Impact	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	175	°C	ASTM D648
Continuous Use Temperature	280	°C	UL 746B
Glass Transition Temperature	152	°C	ASTM D3418
Melting Temperature	372	°C	ASTM D3418
Flammability	Nominal Value		Test Method
Flame Rating (0.800 mm)	V-0		UL 94
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (400°C, 1000 sec ⁻¹)	300	Pa·s	ASTM D3835
Injection	Nominal Value	Unit	
Drying Temperature	150	°C	
Drying Time	4.0 to 6.0	hr	
Hopper Temperature	60.0 to 80.0	°C	
Nozzle Temperature	400	°C	
Processing (Melt) Temp	390 to 400	°C	
Mold Temperature	200 to 220	°C	
NOTE			
1.	400°C nozzle, 220°C Mold		
2.	400°C nozzle, 210°C Mold		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

