RANPELEN J-560S

Polypropylene Random Copolymer Lotte Chemical Corporation

Message:

J-560S is a nucleated random copolymer for injection molding applications. This grade is designed to be processed in conventional injection molding equipment and offers super excellent transparency, good stiffness/impact strength balance, high gloss, high hinge property and low smell.

General Information			
Additive	Nucleating Agent		
Features	Good Impact Resistance		
	Good Stiffness		
	High Clarity		
	High Gloss		
	Low to No Odor		
	Nucleated		
	Random Copolymer		
Uses	Caps		
	Containers		
	Food Containers		
	Media Packaging		
	Stationary Supplies		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ASTM D1238, ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	95		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield	29.4	MPa	ASTM D638
Yield	26.5	MPa	ISO 527-2
Tensile Elongation (Break)	> 100	%	ASTM D638, ISO 527-2
Flexural Modulus			
	1180	MPa	ASTM D790
	971	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

-10°C	25	J/m	ISO 180
-10°C	29	J/m	ASTM D256
23°C	54	J/m	ASTM D256
23°C	49	J/m	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	95.0	°C	ASTM D648
0.45 MPa, Unannealed 0.45 MPa, Unannealed	95.0 85.0	°C	ASTM D648 ISO 75-2/B
·			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

