## Mirathane<sup>™</sup> E375

## Thermoplastic Polyurethane Elastomer (Polyester)

Miracll Chemicals Co., Ltd.

## Message:

Mirathane<sup>™</sup> E375 is a Thermoplastic Polyurethane Elastomer (Polyester) (TPU-Polyester) product. It is available in Asia Pacific. Applications of Mirathane<sup>™</sup> E375 include additive/masterbatch, hose/tubing, consumer goods and engineering/industrial parts. Characteristics include: Fast Molding Cycle Good Processability

General Information			
Features	Fast Molding Cycle		
	Good Processability		
	Low to No Migration		
Uses	Compounding		
	Footwear		
	Hose		
	Overmolding		
	Plastics Modification		
	Tubing		
	Wheels		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method

Durometer Hardness (Shore A)	78		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	4.00	MPa	
300% Strain	8.00	MPa	
Tensile Strength (Yield)	25.0	MPa	ASTM D412
Tensile Elongation (Break)	600	%	ASTM D412
Tear Strength	70.0	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-30.0	°C	DSC

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

