## NYLOY® MS-0200N-3-H

## Polyamide 66

Nytex Composites Co., Ltd.

## Message:

NYLOY®MS-0200N-3-H is a polyamide 66 (nylon 66) material. This product is available in North America or Asia Pacific region. The processing method is injection molding.

| General Information                 |                   |       |             |
|-------------------------------------|-------------------|-------|-------------|
| Processing Method                   | Injection molding |       |             |
| Physical                            | Nominal Value     | Unit  | Test Method |
| Specific Gravity                    | 1.10              | g/cm³ | ASTM D792   |
| Hardness                            | Nominal Value     | Unit  | Test Method |
| Durometer Hardness (Shore D)        | 78                |       | ASTM D2240  |
| Mechanical                          | Nominal Value     | Unit  | Test Method |
| Tensile Strength (Yield)            | 53.8              | MPa   | ASTM D638   |
| Tensile Elongation (Break)          | 50                | %     | ASTM D638   |
| Flexural Modulus                    | 2200              | MPa   | ASTM D790   |
| Flexural Strength                   | 88.1              | MPa   | ASTM D790   |
| Impact                              | Nominal Value     | Unit  | Test Method |
| Notched Izod Impact (23°C, 3.18 mm) | 180               | J/m   | ASTM D256   |
| Injection                           | Nominal Value     | Unit  |             |
| Drying Temperature                  | 110               | °C    |             |
| Drying Time                         | 1.0               | hr    |             |
| Rear Temperature                    | 270               | °C    |             |
| Middle Temperature                  | 280               | °C    |             |
| Nozzle Temperature                  | 290               | °C    |             |
| Mold Temperature                    | 80                | °C    |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

