

LEXAN™ XHT1141 resin

Polycarbonate
SABIC Innovative Plastics

Message:

XHT1141 is a high flow, high heat polycarbonate copolymer. It is the lowest heat product in the LEXAN XHT portfolio. It is available in a range of opaque and limited transparent colors.

General Information			
Features	Copolymer		
	High Flow		
	High Heat Resistance		
Appearance	Clear/Transparent		
	Colors Available		
	Opaque		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR)			ISO 1133
300°C/1.2 kg	16.0	cm ³ /10min	
330°C/2.16 kg	70.0	cm ³ /10min	
Molding Shrinkage - Flow (3.20 mm)	0.60 to 0.90	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	0.30	%	
Equilibrium, 23°C, 50% RH	0.30	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2400	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	65.0	MPa	
Break	60.0	MPa	
Tensile Strain			ISO 527-2/50
Yield	6.5	%	
Break	80	%	
Flexural Modulus ¹	2400	MPa	ISO 178
Flexural Stress	100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ²			ISO 179/1eA
-30°C	12	kJ/m ²	
23°C	16	kJ/m ²	

Charpy Unnotched Impact Strength ³			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Notched Izod Impact Strength ⁴			ISO 180/1A
-30°C	10	kJ/m²	
23°C	14	kJ/m²	
Unnotched Izod Impact Strength ⁵			ISO 180/1U
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁶			
0.45 MPa, Unannealed, 64.0 mm Span	144	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 64.0 mm Span	132	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	150	°C	ISO 306/B50
--	152	°C	ISO 306/B120
CLTE			ISO 11359-2
Flow : -40 to 40°C	7.0E-5	cm/cm/°C	
Transverse : -40 to 40°C	7.0E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	125	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 to 60	%	
Rear Temperature	270 to 305	°C	
Middle Temperature	280 to 325	°C	
Front Temperature	290 to 335	°C	
Nozzle Temperature	285 to 330	°C	
Processing (Melt) Temp	290 to 335	°C	
Mold Temperature	85.0 to 130	°C	
Back Pressure	0.300 to 0.700	MPa	
Screw Speed	40 to 90	rpm	
Vent Depth	0.025 to 0.080	mm	
NOTE			
1.	2.0 mm/min		
2.	80*10*3 sp=62mm		
3.	80*10*3 sp=62mm		
4.	80*10*3		
5.	80*10*3		
6.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

