

TECHNYL® C 216 V30 BLACK Z/4

Polyamide 6
Solvay Engineering Plastics

Message:

TECHNYL® C 216 V30 Black Z/4 is a polyamide 6, reinforced with 30% of glass fibre, for injection moulding. This product is available in black color.

General Information				
UL YellowCard		E44716-235521		
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Agency Ratings		UU 453/2010/EC		
RoHS Compliance		RoHS Compliant		
Appearance		Black		
Processing Method		Injection Molding		
Part Marking Code (ISO 11469)		>PA6-GF30<		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.36	--	g/cm ³	ISO 1183/A
Molding Shrinkage				ISO 294-4
Across Flow	0.35	--	%	
Flow	0.65	--	%	
Water Absorption (23°C, 24 hr)	1.1	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	9600	6200	MPa	ISO 527-2/1A
Tensile Stress (Break)	190	110	MPa	ISO 527-2/1A
Tensile Strain (Break)	3.8	4.5	%	ISO 527-2/1A
Flexural Modulus				
--	8000	--	MPa	ASTM D790
--	9500	5500	MPa	ISO 178
Flexural Strength	235	--	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	15	32	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	100	110	kJ/m ²	ISO 179/1eU
Notched Izod Impact				
23°C	120	--	J/m	ASTM D256
23°C	14	24	kJ/m ²	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	210	--	°C	ASTM D648, ISO 75-2/Af
Melting Temperature	222	--	°C	ISO 11357-3

Peak Crystallization Temperature	190	--	°C	ISO 11357-3
CLTE - Flow (23 to 85°C)	3.2E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	1.0E+11	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+11	ohms·cm	IEC 60093
Electric Strength	--	22	kV/mm	IEC 60243-1
Relative Permittivity	3.80	4.50		IEC 60250
Dissipation Factor	0.020	0.090		IEC 60250
Comparative Tracking Index				IEC 60112
Solution A	600	600	V	
Solution B	475	--	V	
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.800 mm	HB	--		
3.20 mm	HB	--		
Glow Wire Flammability Index (1.60 mm)	650	--	°C	IEC 60695-2-12
Oxygen Index	23	--	%	ISO 4589-2
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Suggested Max Moisture	0.20		%	
Rear Temperature	230 to 235		°C	
Middle Temperature	235 to 245		°C	
Front Temperature	245 to 250		°C	
Mold Temperature	70.0 to 100		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

