Exxtral[™] Performance Polyolefin HMU210

Polypropylene, Compounded (TPO)

ExxonMobil Chemical

Message:

A special thermoplastic polyolefin black resin with high rigidity is suitable for automotive HVAC and parts under the hood.

| General Information | | | |
|--|---------------------------------|-----------|--------------|
| Features | Good dimensional stability | | |
| | Good heat aging resistance | | |
| | | | |
| Uses | Parts under the hood of a car | | |
| | Application in Automobile Field | | |
| | Car interior parts | | |
| Appearance | Black | | |
| Forms | Particle | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.05 | g/cm³ | ISO 1183 |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 12 | g/10 min | ISO 1133 |
| Melt Volume-Flow Rate (MVR) (230°C/2.16 | | | |
| kg) | 14.0 | cm³/10min | ISO 1133 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus - Secant | 2910 | MPa | ISO 527-2 |
| Tensile Stress (Yield) | 33.7 | MPa | ISO 527-2/50 |
| Tensile Strain (Yield) | 5.2 | % | ISO 527-2/50 |
| Flexural Modulus | 2940 | MPa | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength (23°C, Complete Break) | 3.3 | kJ/m² | ISO 179 |
| Thermal | Nominal Value | Unit | Test Method |
| Heat Deflection Temperature | | | |
| 0.45 MPa, not annealed | 116 | °C | ISO 75-2/B |
| 1.8 MPa, not annealed | 63.0 | °C | ISO 75-2/A |
| Additional Information | | | · |

Unless otherwise specified herein: data were prepared pursuant to ExxonMobil's sampling and testing procedures in effect at time of production; and applicable sampling and testing methods are available upon request. Values may result from interpolation or correlation of other data.Sampling and testing methods are subject to change without notice unless otherwise agreed in writing.

Legal statement

本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用本产品不宜在与食品接触的应用中使用.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

