

# ARMAMID® PA HC 20

Polyamide 6

Poly Plastic

Message:

ARMAMID® PA HC 20 is a Polyamide 6 (Nylon 6) product. It is available in Europe.

General Information		
Physical	Nominal Value	Unit
Density	1.21	g/cm <sup>3</sup>
Molding Shrinkage	0.60 to 0.80	%
Mechanical	Nominal Value	Unit
Tensile Stress (Yield)	140	MPa
Flexural Modulus (23°C)	9500	MPa
Flexural Stress	210	MPa
Impact	Nominal Value	Unit
Charpy Unnotched Impact Strength (20°C)	20	kJ/m <sup>2</sup>
Thermal	Nominal Value	Unit
Melting Temperature	218	°C
Heat Stability - of wick	210	°C
Electrical	Nominal Value	Unit
Surface Resistivity <sup>1</sup>	1.0E+2	ohms
Volume Resistivity <sup>2</sup>	1.1E+4	ohms·cm
NOTE		
1.	Dry	
2.	Dry	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

  
WECHAT