

DynaMix™ 2035-L

Polyamide 66

Polymer Dynamix

Message:

Modified Glass-Filled PA66

Features:

Excellent Flow Properties

Good Dimensional Stability

Heat Stabilized

Applications:

Automotive

Small Appliances

Industrial

General Information	
Filler / Reinforcement	Glass Fiber
Additive	Heat Stabilizer
Features	Good Dimensional Stability
	Good Flow
	Heat Stabilized
Uses	Appliance Components
	Appliances
	Automotive Applications
	Industrial Applications

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.46	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	216	MPa	
Break	216	MPa	
Tensile Elongation			ASTM D638
Yield	6.5	%	
Break	7.5	%	
Flexural Modulus	13800	MPa	ASTM D790
Flexural Strength	331	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	150	J/m	ASTM D256

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

