Ebalta GM 956 / Comp. A+B

Polyurethane

Ebalta Kunststoff GmbH

Message:

This product is a polyurethane system.

By mixing of hardeners shore hardness between A 38 and A 83can be reached.

The product can be subject to colour variations due to raw materials, but these colour variations have no influence on the quality and the properties of the product.

Applications

Prototypes with rubber-like properties

Flexible parts

Properties

shore A hardness 30

shore hardness (flexibility) variable till A 83

excellent flow properties

transparent

easily dyeable

odourless

free of mercury

high tear strength

General Information			
Features	Good Colorability		
	Good Flexibility		
	Good Tear Strength		
	High Clarity		
	High Flow		
	Low to No Odor		
Uses	Prototyping		
Appearance	Clear/Transparent		
Processing Method	Casting		
Hardness	Nominal Value		Test Method
Shore Hardness (Shore A)	28 to 32		ISO 7619
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (Yield)	2.00 to 2.40	MPa	ISO 37
Tensile Elongation ² (Break)	1500 to 2500	%	ISO 37
Tear Strength ³ (1.00 mm)	6.2 to 7.2	kN/m	ISO 34-1
Thermoset	Nominal Value	Unit	
Thermoset Components			
Hardener	Mix Ratio by Weight: 200		
Resin	Mix Ratio by Weight: 100		
Uncured Properties	Nominal Value	Unit	
Density (20°C)	1.02 to 1.06	g/cm³	
Viscosity (25°C)	1.3 to 1.7	Pa·s	

Curing Time (70°C)	3.0	hr	
Curing Time (70°C) Pot Life ⁴ (20°C)	20 to 30	min	
NOTE			
1.	Type 2		
2.	Type 2		
	Arch shaped test piece v	with	
3.	incision		
4.	200 g		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

