

Nypol® PA A3 G15 FR HS NTLA013 NR336

Polyamide 66

Petropol Industry and Trade of Polymers LTDA

Message:

Polyamide 6.6 Natural reinforced with 15% glass fiber, anti-flame (V-0), thermally stable, good set of thermal and mechanical properties. Ideal for injection molding.

General Information			
Filler / Reinforcement	Glass Fiber, 15% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Thermal Stability		
Appearance	Black		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	>PA 66 GF15<		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.60 to 0.90	%	ASTM D955
Water Absorption (24 hr)	1.3	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	120	MPa	ASTM D638
Tensile Elongation (Break)	3.5	%	ASTM D638
Flexural Modulus	4900	MPa	ASTM D790
Flexural Strength	165	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	42	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	238	°C	ASTM D648
Melting Temperature	260	°C	ASTM D2117
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.020	%	
Processing (Melt) Temp	260 to 280	°C	
Mold Temperature	70.0 to 100	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

