

4PROP® 9C11120 XHFR3

Polypropylene Copolymer
4Plas

Message:

4PROP 9C11120 XHFR3 is a MFI 15 20% Talc Filled UL Listed FR-V2, Heat Stabilised Copolymer Polypropylene

General Information			
Filler / Reinforcement	Talc filler, 20% filler by weight		
Additive	heat stabilizer		
Features	Copolymer		
	Thermal Stability		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.09	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2250	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	25.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	40	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	4.0	kJ/m ²	ISO 180/1A
23°C	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	75	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	55.0	°C	ISO 75-2/A
Melting Temperature ¹	165	°C	ISO 11357
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	V-2		UL 94
1.60 mm	V-2		UL 94
Glow Wire Flammability Index (2.00 mm)	850	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (2.00 mm)	775	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Processing (Melt) Temp	200 - 240	°C	

Mold Temperature	20.0 - 50.0	°C
Injection Rate	Moderate	
Holding Pressure	40.0 - 80.0	MPa
Screw Speed	200	rpm

Injection instructions

Feed Throat Temperature: 20 - 60 °CBack Pressure: Low

NOTE

1.
- 10 K/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

