ARCEL® 730B (3.00 pcf)

Polystyrene + PE

NOVA Chemicals

Message:

ARCEL® 730B (3.00 pcf) is a Polystyrene + PE (PS+PE) material. It is available in North America for foam processing. Typical application of ARCEL® 730B (3.00 pcf): Foam

| General Information | | | |
|---------------------------------|-----------------|--------|--------------|
| Features | Expandable | | |
| Uses | Foam | | |
| Appearance | Natural Color | | |
| | White | | |
| Forms | Spheres | | |
| Processing Method | Foam Processing | | |
| Physical Physical | Nominal Value | Unit | Test Method |
| Density | 0.0481 | g/cm³ | ASTM D3575 |
| Particle Size - 98% | 0.800 to 1.70 | mm | A311VI D3373 |
| | 0.000 to 1.70 | 111111 | |
| VOC Content | | | |
| Pentane | 11 | % | |
| Plasticizer | 0.30 | % | |
| Flexural Strain | 9.4 | % | ASTM C203 |
| Tear Strength - at Maximum Load | 3.9 | kN/m | ASTM D3575 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | 0.645 | MPa | ASTM D3575 |
| Flexural Strength | | | ASTM C203 |
| | 0.656 | MPa | |
| 5.0% Strain | 0.600 | MPa | |
| Compressive Strength | | | ASTM D3575 |
| 10% Strain | 0.299 | MPa | |
| 25% Strain | 0.341 | MPa | |
| 50% Strain | 0.418 | MPa | |
| 75% Strain | 0.811 | MPa | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

