

# Generic SBR, Unspecified

Styrene Butadiene Rubber

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic SBR, Unspecified  
This information is provided for comparative purposes only.

General Information			
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.920 to 1.00	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	60 to 100	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (23°C)	40 to 80		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	3.00 to 23.0	MPa	ASTM D412
Tensile Elongation (Break, 23°C)	380 to 650	%	ASTM D412
Tear Strength (23°C)	34.7 to 35.6	kN/m	ASTM D624

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT