

KumhoSunny PC/ABS HAC5010G

Polycarbonate + ABS

Shanghai KumhoSunny Plastics Co., Ltd.

Message:

HAC5010G is a good dimensional stability glass fiber reinforced PC/ABS resin .

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Good Dimensional Stability		
Uses	Business Equipment		
	Printer		
	Printer Parts		
UL File Number	E254819		
	E65424		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.20	g/cm ³	ASTM D792
--	1.19	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/10.0 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage			
Flow	0.30 to 0.50	%	ASTM D955
--	0.30 to 0.50	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
--	70.0	MPa	ASTM D638
--	65.0	MPa	ISO 527-2/5
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus			
--	4000	MPa	ASTM D790
-- ¹	3500	MPa	ISO 178
Flexural Strength			
--	110	MPa	ASTM D790
-- ²	110	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ³ (23°C)	10	kJ/m ²	ISO 179

Notched Izod Impact			
3.20 mm	130	J/m	ASTM D256
23°C ⁴	9.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed	110	°C	ASTM D648
1.8 MPa, Unannealed ⁵	112	°C	ISO 75-2/A
Vicat Softening Temperature			
--	122	°C	ASTM D1525 ⁶
--	120	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	100 to 110	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	< 0.020	%	
Rear Temperature	220 to 240	°C	
Middle Temperature	240 to 260	°C	
Front Temperature	260 to 270	°C	
Nozzle Temperature	250 to 260	°C	
Processing (Melt) Temp	260 to 270	°C	
Mold Temperature	60.0 to 80.0	°C	
Back Pressure	0.300 to 1.00	MPa	
Screw Speed	30 to 70	rpm	
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		
3.	4J		
4.	5.5J		
5.	120°C/h		
6.	Rate B (120°C/h)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

