

# SuperLite® SL552000-100 (6.0mm)

Polypropylene

Azdel, Inc.

## Message:

AZDEL SuperLite SL552000-100 (6.0mm) is a low pressure, thermoformable, thermoplastic composite of polypropylene and long chopped glass fibers. Usually combined with outer layers as needed for the application (i.e.; adhesive films, barrier films, scrim, tough PP films, non-wovens, reinforcements or just the bare surface.) Typically used in non-structural applications where a very high strength to weight ratio is required, such as automotive headliners, door panels, package shelves, and other interior trim.

General Information			
Filler / Reinforcement	Long glass fiber, 55% filler by weight		
Appearance	Black		
	Natural color		
Forms	Sheet		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.359	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	< 0.020	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2100	MPa	ASTM D638
Tensile Strength	18.0	MPa	ASTM D638
Impact	Nominal Value	Unit	Test Method
Instrumented Dart Impact			ASTM D3763
23°C, Energy at Peak Load	7.90	J	ASTM D3763
23°C, Total Energy	13.8	J	ASTM D3763

Additional Information			
Multi-axial Impact Peak Force, ASTM D3763, 23°C: 1430 NMass per unit area, Internal Test Method: 2000 g/m <sup>2</sup> Flexual Strength, SAE J949: 9 MPaFlexual Modulus, SAE J949: 1150 MPa			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT