

Lupoy® HI5002A

Polycarbonate + ABS

LG Chem Ltd.

Message:

Lupoy® HI5002A is a Polycarbonate + ABS (PC+ABS) material. It is available in Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of Lupoy® HI5002A are:

Flame Rated

High Flow

Impact Resistant

Typical applications include:

Automotive

Electrical/Electronic Applications

Housings

General Information			
UL YellowCard	E302314-530050	E67171-248467	E248280-322211
Features	E353371-101107251		
	General Purpose		
	High Flow		
	High Impact Resistance		
Uses	Electrical Housing		
	Electrical/Electronic Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	54.9	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	70	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	2060	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 3.20 mm)	84.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	560	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	104	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	80.0 to 100	°C
Drying Time	4.0 to 6.0	hr
Minimum Moisture Content	0.020	%
Rear Temperature	230 to 255	°C
Middle Temperature	235 to 265	°C
Front Temperature	235 to 265	°C
Nozzle Temperature	235 to 265	°C
Processing (Melt) Temp	230 to 260	°C
Mold Temperature	50.0 to 70.0	°C
Screw Speed	40 to 70	rpm

NOTE

- | | |
|----|-----------|
| 1. | 50 mm/min |
| 2. | 50 mm/min |
| 3. | 10 mm/min |
| 4. | 10 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT