

Modified Plastics MN 6/6-FG 10

Polyamide 66
Modified Plastics, Inc.

Message:
Modified Plastics MN 6/6-FG 10 is a Polyamide 66 (Nylon 66) product filled with 10% glass fiber. It can be processed by injection molding and is available in North America.

General Information			
UL YellowCard	E78964-250217		
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.7	%	ASTM D955
Water Absorption			ASTM D570
24 hr	1.3	%	
Saturation	7.6	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	89.6	MPa	ASTM D638
Tensile Elongation (Yield)	3.5	%	ASTM D638
Flexural Modulus	4550	MPa	ASTM D790
Flexural Strength (Yield)	138	MPa	ASTM D790
Compressive Strength	117	MPa	ASTM D695
Shear Strength	62.1	MPa	ASTM D732
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.35 mm)	37	J/m	ASTM D256
Unnotched Izod Impact (23°C, 6.35 mm)	270	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	257	°C	
1.8 MPa, Unannealed	249	°C	
Vicat Softening Temperature	265	°C	ASTM D1525
CLTE - Flow	4.5E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength	22	kV/mm	ASTM D149
Dielectric Constant			ASTM D150

100 Hz	4.10	
1 kHz	1.90	
1 MHz	3.70	
Dissipation Factor (1 kHz)	0.030	ASTM D150
Injection	Nominal Value	Unit
Drying Temperature	93.3	°C
Processing (Melt) Temp	271 to 293	°C
Mold Temperature	93.3 to 104	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT