Tenite[™] Acetate 132E5243225 Clear, Trsp

Cellulose Acetate

Eastman Chemical Company

Message:

Tenite[™] cellulosic plastics are noted for their excellent balance of properties - toughness, hardness, strength, surface gloss, clarity, and a warm feel. The mechanical properties if Tenite[™] cellulosic plastics differ with plasticizer levels. Lower plasticizer content yields a harder surface, higher heat resistance, greater rigidity, higher tensile strength, and better dimensional stability. Higher plasticizer content increases impact strength. Tenite[™] cellulosic plastics are available in natural, clear, amber, and black. Color concentrates are available in let-down ratios from 10:1 to 40:1. Tenite[™] Cellulosic Acetate 132-25 has a plasticizer level of 25%.

| General Information | |
|---------------------|----------------------------|
| Additive | Plasticizer (25%) |
| Features | Good Strength |
| | Good Toughness |
| | High Gloss |
| | High Hardness |
| | Plasticized |
| | Renewable Resource Content |
| | Soft |
| | |
| Uses | Eyeglasses |
| Appearance | Amber |
| | Black |
| | Clear/Transparent |
| | Natural Color |
| | |
| Forms | Pellets |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

