# Lifoflex® GB 1050

# Styrene Ethylene Butylene Styrene Block Copolymer

Müller Kunststoffe GmbH

## Message:

The series GA, GB and GC are TPE compounds based on SEBS. They are suited for a lot of different applications and are characterized by an easy processing and high fl exibility. Properties: shore hardness: 20 - 90 Shore A different densities: 0,89 - 1,21 g/ccm translucent, nature colored or direct pigmented materials possible resistant against aqueous solutions, inorganic acids and bases physiologically harmless easy processing in injection molding good adhesion on PP/PE very good mechanical properties service temperature range from -40°C up to 100°C high fl exibility UV resistant (suitable for outdoor use) applications with food contact are possible in conformity with FDA, 10/2011/EC and EN 71/3 (toys) in conformity with European directives 2002/95/EC (RoHS) and 2003/11/EC recyclable Applications: consumer/household: sealings for food storage boxes soft-touch surfaces for packaging 2-component grips for kitchen equipment toys: soft seats for sledge wheels for toy cars toy characters electronics: sealings for housings soft touch coating for housings sports and leisure: bicycle grips soft-touch grips for hiking and nordic walking sticks fins health care: grips for toothbrushes sealings and closures for packaging anti-slip grips for baby tableware

General Information	
Features	Acid Resistant
	Base Resistant
	Food Contact Acceptable
	Good Adhesion
	Good Colorability
	Good Flexibility
	Good Processability
	Good UV Resistance

#### Low Toxicity

Recyclable Material

FDA Unspecified Rating

RoHS Compliance	<b>RoHS</b> Compliant		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Density	1.00	g/cm³	ISO 1183/A
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 3 sec)	50		DIN 53505
Elastomers	Nominal Value	Unit	Test Method
Elastomers Tensile Stress - Flow (Yield)	Nominal Value 6.30	Unit MPa	Test Method DIN 53504
Tensile Stress - Flow (Yield)	6.30	MPa	DIN 53504
Tensile Stress - Flow (Yield) Tensile Elongation - Flow (Break)	6.30	MPa	DIN 53504 DIN 53504
Tensile Stress - Flow (Yield) Tensile Elongation - Flow (Break) Compression Set	6.30 850	MPa %	DIN 53504 DIN 53504

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

