

# Durez® 13848

Phenolic

Sumitomo Bakelite North America, Inc.

## Message:

Durez 13848 is a finely pulverized two-step thermosetting phenolic resin. It has a long flow, a medium cure and a rigid set.

Durez 13848 is recommended for use in Friction applications.

General Information			
Uses	Gears		
	Pulleys		
Thermoset	Nominal Value	Unit	Test Method
Post Cure Time (165°C)	8.1E-3	hr	
Additional Information	Nominal Value	Unit	Test Method
Hexa	8.5	%	Internal Method
Inclined Plate Flow (125°C)	8.10	cm	Internal Method
Screen Mesh <sup>1</sup>	< 1.0	%	Internal Method
NOTE			
1.	200 Mesh		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

