LTP ZW-3210

Acetal (POM) Copolymer

Chengdu Letian Plastics Co., Ltd

Message:

Resin of LTP ZW-3200 serials is crystal whisker reinforced composite materials based on Polyformaldehyde. With the characteristics of outstanding thermal stability, self-lubricating and frost resisting, the materials can be used long time about 20°C lower than the Temperature of thermal deformation without any lubrication additive. And it is the first choice for parts of rolling and sliding machine.

Compare to Polyformaldehyde, Resin of LTP ZW-3200 serials have good mold technology without irritating smell and its products are according with RoHS index.

| General Information | | | |
|-------------------------------------|------------------------|-------|-------------|
| Features | Good Thermal Stability | | |
| | Good Wear Resistance | | |
| | Self Lubricating | | |
| RoHS Compliance | RoHS Compliant | | |
| Appearance | Colors Available | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.50 | g/cm³ | GB/T 1033 |
| Molding Shrinkage ¹ | | | |
| Across Flow: 3.00 mm | 0.80 to 1.2 | % | |
| Flow: 3.00 mm | 0.50 to 0.80 | % | |
| Water Absorption (Saturation, 23°C) | 0.30 | % | GB/T 1034 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Stress | 100 | MPa | GB/T 1040 |
| Tensile Strain (Break) | 1.2 to 2.5 | % | GB/T 1040 |
| Flexural Stress | 110 | MPa | GB/T 1042 |
| Coefficient of Friction | 0.10 to 0.15 | | ASTM D1894 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength | 8.0 | kJ/m² | GB/T 1043 |
| NOTE | | | |
| 1. | 80x80x3 mm | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

