

Unipren® Elastomers A3 PRTA010 65A IM06S1 UP338

Styrene Ethylene Butylene Styrene Block Copolymer
Petropol Industry and Trade of Polymers LTDA

Message:

Unipren® Elastomers A3 PRTA010 65A IM06S1 UP338 is a Styrene Ethylene Butylene Styrene Block Copolymer (SEBS) material. It is available in Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of Unipren® Elastomers A3 PRTA010 65A IM06S1 UP338 are:

- Chemical Resistant
- Good Processability
- Good UV Resistance

Typical applications include:

- Consumer Goods
- Household Applications
- Tools

General Information			
Features	Good Chemical Resistance		
	Good Processability		
	Good UV Resistance		
	Ozone Resistant		
	Soft		
Uses	Household Goods		
	Power/Other Tools		
	Toys		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.980	g/cm ³	ASTM D792
Molding Shrinkage - Flow	2.0 to 3.0	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	62 to 68		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹			ASTM D412
100% Strain	2.00	MPa	
300% Strain	3.00	MPa	
Tensile Strength ² (Break)	7.00	MPa	ASTM D412
Tensile Elongation ³ (Break)	> 600	%	ASTM D412
Tear Strength ⁴	40.0	kN/m	ASTM D624
Compression Set (70°C, 22 hr)	55	%	ASTM D395B
Injection	Nominal Value	Unit	

Drying Temperature	80.0	°C
Drying Time	2.0	hr
Processing (Melt) Temp	170 to 190	°C
Mold Temperature	20.0 to 50.0	°C

NOTE

- | | |
|----|-------|
| 1. | Die C |
| 2. | Die C |
| 3. | Die C |
| 4. | Die B |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

