

Generic Nylon 6+PP

Polyamide 6 + PP

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic Nylon 6+PP
This information is provided for comparative purposes only.

General Information			
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	1200 to 6800	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3.5 to 6.7	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0 to 17	kJ/m²	ISO 179

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT