

# Primefin V515R35

Polypropylene  
Lucent Polymers, Inc.

Message:  
35% Glass/Mineral Reinforced, Chemically Coupled, Impact Modified Polypropylene  
Colors Available  
Meets GMP.PP.032

General Information			
Filler / Reinforcement	Glass\Mineral,35% Filler by Weight		
Additive	Impact Modifier		
Features	Chemically Coupled		
	Impact Modified		
Appearance	Colors Available		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.40	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	44.8	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	3790	MPa	ASTM D790
Flexural Strength	55.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	132	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT