

Kinta FR3600B

Acrylonitrile Butadiene Styrene
Kinta Technology (Hong Kong) Co., Ltd.

Message:

Kinta FR3600B is an acrylonitrile butadiene styrene (ABS) product. It is available in the Asia-Pacific region. The main characteristics are: flame retardant/rated flame.

General Information			
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.17	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	21	g/10 min	ASTM D1238
Molding Shrinkage - Flow (23°C)	0.30 - 0.50	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	36.0	MPa	ASTM D638
Tensile Elongation ² (Break)	16	%	ASTM D638
Flexural Modulus ³	2000	MPa	ASTM D790
Flexural Strength ⁴	67.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	18.0	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	80.0	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.6 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	70 - 80	°C	
Drying Time	4.0 - 6.0	hr	
Rear Temperature	200 - 210	°C	
Middle Temperature	205 - 210	°C	
Front Temperature	200 - 210	°C	
Processing (Melt) Temp	190 - 210	°C	
Mold Temperature	40 - 80	°C	
Injection Rate	Moderate-Fast		
NOTE			
1.	20 mm/min		
2.	20 mm/min		
3.	5.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

