

LNP™ STAT-LOY™ AF306 compound

Acrylonitrile Butadiene Styrene

SABIC Innovative Plastics

Message:

LNP* STAT-LOY* AF306 is a compound based on ABS resin containing 30% Glass Fiber. Added feature of this material is: Antistatic.

Also known as: LNP* STAT-LOY* Compound AF-30

Product reorder name: AF306

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Antistatic		
Features	Antistatic		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.29	g/cm ³	ASTM D792
--	1.28	g/cm ³	ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.20 to 0.40	%	ASTM D955
Across Flow : 24 hr	0.40 to 0.60	%	ASTM D955
Across Flow : 24 hr	0.45	%	ISO 294-4
Flow : 24 hr	0.30	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	3.0	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	6890	MPa	ASTM D638
--	6010	MPa	ISO 527-2/1
Tensile Strength			
Yield	38.6	MPa	ASTM D638
Yield	43.0	MPa	ISO 527-2
Break	38.6	MPa	ASTM D638
Break	43.0	MPa	ISO 527-2
Tensile Elongation			
Yield	1.0	%	ASTM D638
Yield	1.1	%	ISO 527-2
Break	1.0	%	ASTM D638
Break	1.1	%	ISO 527-2
Flexural Modulus			
--	5520	MPa	ASTM D790
--	5700	MPa	ISO 178
Flexural Strength			

--	48.3	MPa	ASTM D790
--	63.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	48	J/m	ASTM D256
23°C ²	5.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	250	J/m	ASTM D4812
23°C ³	17	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	6.90	J	ASTM D3763
--	1.70	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	102	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁴	103	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	95.6	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	71.0	°C	ISO 75-2/Af
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	1.1E-4	cm/cm/°C	
Transverse : -40 to 40°C	4.3E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+10 to 1.0E+12	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	71.1 to 82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.050 to 0.10	%	
Rear Temperature	182 to 193	°C	
Middle Temperature	193 to 204	°C	
Front Temperature	204 to 216	°C	
Processing (Melt) Temp	199 to 210	°C	
Mold Temperature	10.0 to 48.9	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

