

LNP™ LUBRICOMP™ LX00430 compound

Polyetheretherketone

SABIC Innovative Plastics

Message:

LNP* LUBRICOMP* LX00430 is a compound based on Polyetheretherketone containing Proprietary Fillers. Added feature of this grade is: Wear Resistant.

Also known as: LNP* LUBRICOMP* Compound PDX-L-00430

Product Reorder name: LX00430

General Information		
Filler / Reinforcement	Proprietary	
Features	Good Wear Resistance	
Processing Method	Injection Molding	
Injection	Nominal Value	Unit
Drying Temperature	150	°C
Drying Time	4.0 to 6.0	hr
Rear Temperature	370 to 380	°C
Middle Temperature	380 to 400	°C
Front Temperature	380 to 400	°C
Mold Temperature	175 to 190	°C
Back Pressure	0.300 to 0.700	MPa
Screw Speed	60 to 100	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT