## POLYTROPE® STR 3567EU-01 CLEAR

Enhanced Polyolefin (Capstock Resin)

A. Schulman Inc.

## Message:

POLYTROPE STR 3567EU resin is a medium gloss, weatherable, olefin cap resin providing exceptional durability. It is specifically designed for the co-extrusion process as a cap resin over POLYTROPE STR enhanced polyolefin TPO and FR TPO base resins. It is especially suited for thermoformed applications, as it maintains its' smooth surface and uniform gloss through the thermoforming process. POLYTROPE STR 3567EU-01 CLEAR can be used as a clear cap or it can be easily colored. The durability of the cap resin enables it match or exceed the performance of acrylic resins, laminated films, and paint coatings.

General Information				
Features	Durable			
	Good Chemical Resistance			
	Good Weather Resistance			
	High Scratch Resistance			
	Low Temperature Impact Resistance			
	Recyclable Material			
	Stain Resistant			
Forms	Pellets			
Processing Method	Coextrusion			
	Extrusion			
	Profile Extrusion			
	Sheet Extrusion			
	Thermoforming			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity <sup>1</sup>	0.898	g/cm <sup>3</sup>	ISO 1183	
Melt Mass-Flow Rate (MFR) (230°C/2.16	0.030	g/cm	150 1105	
kg)	2.5	g/10 min	ISO 1133	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Stress <sup>2</sup> (Yield, 23°C)	42.1	MPa	ISO 527-2	
Tensile Strain <sup>3</sup> (Break, 233°C)	200	%	ISO 527-2	
Flexural Modulus - Chord <sup>4</sup> (23°C)	2070	MPa	ISO 178	
Impact	Nominal Value	Unit	Test Method	
Instrumented Dart Impact (23°C, Total Energy, Ductile Failure)	46.3	J	ASTM D3763	
Thermal	Nominal Value	Unit	Test Method	
Heat Deflection Temperature (0.45 MPa, Unannealed)	92.2	°C	ISO 75-2/Bf	
Flammability	Nominal Value		Test Method	
Flame Rating (3.18 mm, All Colors)	НВ		UL 94	

Optical	Nominal Value	Test Method
Gardner Gloss (60°, 3180 µm, Thermoformed, Smooth)	60 to 70	ISO 2813
NOTE		
1.	Method A	
2.	Type 1, 50 mm/min	
3.	Type 1, 50 mm/min	
4.	Type 1A, 2.0 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

