

SUPREME Specialty PS SP6489 9940

High Impact Polystyrene

Supreme Petrochem Ltd.

Message:

SUPREME Specialty PS SP6489 9940 is a High Impact Polystyrene product. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, or North America. Applications of SUPREME Specialty PS SP6489 9940 include food contact applications and housings.

Characteristics include:

Flame Rated

Good Toughness

High Flow

General Information			
Features	Good Toughness		
	High Flow		
Uses	Television Housings		
Agency Ratings	FDA 21 CFR 177.1640		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	6.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (23°C, 3.20 mm, Injection Molded)	28.0	MPa	ASTM D638
Tensile Elongation ² (Break, 23°C, 3.20 mm, Injection Molded)	35	%	ASTM D638
Flexural Modulus (23°C, 3.20 mm, Injection Molded)	2000	MPa	ASTM D790
Flexural Strength (23°C, 3.20 mm, Injection Molded)	50.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm, Injection Molded)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm, Injection Molded)	79.0	°C	ASTM D648
Vicat Softening Temperature	96.0	°C	ASTM D1525 ³
Flammability	Nominal Value	Test Method	
Flame Rating (1.60 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Processing (Melt) Temp	180 to 260	°C	

Mold Temperature	40.0 to 60.0	°C
NOTE		
1.	50 mm/min	
2.	50 mm/min	
3.	Rate B (120°C/h), Loading 1 (10 N)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

