

ULTEM™ 2312EPR resin

Polyether Imide

SABIC Innovative Plastics

Message:

30% Milled glass filled, high flow Polyetherimide (Tg 217C) with internal mold release and enhanced electroplatability. ECO Conforming, UL94 V0 listing.

General Information			
Filler / Reinforcement	Glass fiber with embossing, 30% filler by weight		
Additive	demoulding		
Features	Comply with ECO		
	Electroplateable		
	High liquidity		
Agency Ratings	EU Eco		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.48	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	14	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (360°C/5.0 kg)	14.0	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal method
Flow ¹	0.40 - 0.60	%	Internal method
Flow: 3.20mm	0.40 - 0.60	%	Internal method
Transverse flow: 3.20mm	0.40 - 0.60	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.90	%	ISO 62
Equilibrium, 23°C, 50% RH	0.50	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ²	6480	MPa	ASTM D638
--	5300	MPa	ISO 527-2/1
Tensile Strength			
Yield ³	94.8	MPa	ASTM D638
Yield	80.0	MPa	ISO 527-2/5
Fracture ⁴	94.8	MPa	ASTM D638
Fracture	80.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁵	2.0	%	ASTM D638
Yield	2.0	%	ISO 527-2/5
Fracture ⁶	2.0	%	ASTM D638

Fracture	2.0	%	ISO 527-2/5
Flexural Modulus			
50.0mm span ⁷	5580	MPa	ASTM D790
-- ⁸	5500	MPa	ISO 178
Flexural Stress			
--	145	MPa	ISO 178
Yield, 50.0mm span ⁹	156	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹⁰			ISO 179/1eA
-30°C	4.0	kJ/m ²	ISO 179/1eA
23°C	5.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ¹¹			ISO 179/1eU
-30°C	25	kJ/m ²	ISO 179/1eU
23°C	25	kJ/m ²	ISO 179/1eU
Notched Izod Impact			
23°C	40	J/m	ASTM D256
-30°C ¹²	5.0	kJ/m ²	ISO 180/1A
23°C ¹³	5.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	330	J/m	ASTM D4812
-30°C ¹⁴	25	kJ/m ²	ISO 180/1U
23°C ¹⁵	25	kJ/m ²	ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	15.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	204	°C	ASTM D648
0.45 MPa, unannealed, 6.40mm	206	°C	ASTM D648
0.45 MPa, unannealed, 64.0mm span ¹⁶	204	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 3.20mm	199	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	202	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹⁷	192	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	216	°C	ASTM D1525 ¹⁸
--	211	°C	ISO 306/B50
--	213	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			
Flow: -40 to 150°C	3.2E-5	cm/cm/°C	ASTM E831
Flow: 23 to 150°C	3.2E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 150°C	3.5E-5	cm/cm/°C	ASTM E831
Horizontal: 23 to 150°C	3.5E-5	cm/cm/°C	ISO 11359-2

Thermal Conductivity	0.32	W/m/K	ISO 8302
Electrical	Nominal Value		Test Method
Arc Resistance ¹⁹	PLC 5		ASTM D495
Comparative Tracking Index (CTI)	PLC 4		UL 746
High Amp Arc Ignition (HAI)	PLC 4		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 4		UL 746
Hot-wire Ignition (HWI)	PLC 4		UL 746
Flammability	Nominal Value		Test Method
Flame Rating (0.400 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	4.0 - 6.0	hr	
Drying Time, Maximum	24	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	332 - 399	°C	
Middle Temperature	338 - 399	°C	
Front Temperature	343 - 399	°C	
Nozzle Temperature	343 - 399	°C	
Processing (Melt) Temp	349 - 399	°C	
Mold Temperature	135 - 163	°C	
Back Pressure	0.345 - 0.689	MPa	
Screw Speed	40 - 70	rpm	
Vent Depth	0.025 - 0.076	mm	
NOTE			
1.	Tensile Bar		
2.	5.0 mm/min		
3.	Type 1, 5.0 mm/min		
4.	Type 1, 5.0 mm/min		
5.	Type 1, 5.0 mm/min		
6.	Type 1, 5.0 mm/min		
7.	1.3 mm/min		
8.	2.0 mm/min		
9.	1.3 mm/min		
10.	80*10*4 sp=62mm		
11.	80*10*4 sp=62mm		
12.	80*10*4		
13.	80*10*4		
14.	80*10*4		
15.	80*10*4		
16.	80*10*4 mm		
17.	80*10*4 mm		

18.	标准 B (120°C/h), 载荷2 (50N)
19.	Tungsten electrode

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

