

INEOS PP 200-CA70

Polypropylene Random Copolymer

INEOS Olefins & Polymers Europe

Message:

- Benefits & Features
- 200-CA70 is a very high flow clarified random copolymer with a medium ethylene content specifically designed for the production of clear thin-walled injection-moulded articles.
- Clarified
- Antistatic
- Very high flow
- Applications
- Housewares
- Transparent thin wall injection moulding
- Clarified food containers

General Information			
Additive	Antistatic		
	Clarifier		
Features	Antistatic		
	High Clarity		
	High Flow		
	Random Copolymer		
Uses	Food Containers		
	Household Goods		
	Thin-walled Parts		
RoHS Compliance	Contact Manufacturer		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	70	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C, Injection Molded)	28.0	MPa	ISO 527-2
Flexural Modulus (23°C, Injection Molded)	1100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/A
0°C, Injection Molded	2.8	kJ/m²	
23°C, Injection Molded	4.0	kJ/m²	
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (0.45 MPa, Unannealed)	83.0	°C	ISO 75-2/B
Vicat Softening Temperature	128	°C	ISO 306/A50
Peak Crystallization Temperature (DSC)	119	°C	Internal Method
Optical	Nominal Value	Unit	Test Method
Haze			ASTM D1003
1000 μm	15	%	
2000 μm	30	%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

