Topilene® HJ801R

Polypropylene Homopolymer

Hyosung Corporation

Message:

Characteristics:

High Stiffness

Long term heat resistance, UL 746B

Applications:

Toaster

Coffee maker

Steam iron

General Information	
Features	Good Stiffness
	High Heat Resistance
	Homopolymer
Uses	Appliances
	Electrical/Electronic Applications
	Household Goods

Physical	Nominal Value	Unit	Test Method	
Melt Mass-Flow Rate (MFR) (230°C/2.16				
kg)	11	g/10 min	ASTM D1238	
Mechanical	Nominal Value	Unit	Test Method	
Flexural Modulus	2160	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Unnotched Izod Impact (23°C)	34	J/m	ASTM D256	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

