

4MID® 9A20500 FR7

Polyamide 66

4Plas

Message:

4MID 9A20500 FR7 is a Standard Flow Heat Stabilised FR-V2 Halogen Free PA66

General Information			
Additive	heat stabilizer		
Features	Thermal Stability		
	Halogen-free		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183
Molding Shrinkage - Flow	1.3 - 1.4	%	
Water Absorption ¹ (Equilibrium, 23°C, 50% RH)	2.2	%	ISO 62
Moisture Content	< 2000	ppm	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3500	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	80.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	5.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	4.0	kJ/m ²	ISO 180/1A
23°C	5.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	210	°C	ISO 75-2/B
1.8 MPa, not annealed	75.0	°C	ISO 75-2/A
Vicat Softening Temperature	245	°C	ISO 306/B
Melting Temperature ²	262	°C	ISO 11357
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-2		UL 94
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	

Drying Temperature	80.0	°C
Drying Time	2.0	hr
Suggested Max Moisture	0.20	%
Processing (Melt) Temp	270 - 290	°C
Mold Temperature	50.0 - 90.0	°C
Injection Rate	Moderate-Fast	
Holding Pressure	50.0 - 100	MPa
Screw Speed	400	rpm

Injection instructions

Feed Throat Temperature: 60 - 80 °C Back Pressure: Low

NOTE

1. 24 Hrs
2. 10 K/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

