

ACRYLITE® Sheet Soundstop GS CC

Acrylic

Evonik Cyro LLC

Message:

ACRYLITE® Soundstop GS CC is a highly transparent grade of cast acrylic with embedded polyamide threads. In the event of breakage due to an accident, these threads retain any sheet fragments and prevent them from falling down.

Properties

In addition to the well-known and proven properties of ACRYLITE® such as:

excellent light transmission and brilliance

extremely high weather resistance

high surface hardness

low weight - half the weight of glass

11times the impact strength of glass

100% recyclability,

Applications

These properties make ACRYLITE® Soundstop GS CC especially suitable for noise control on highway and railway bridges.

wind barriers on bridges

General Information			
Features	Noise reduction		
	Impact resistance, high		
	Recyclable materials		
	Machinable		
	Good weather resistance		
	Definition, high		
	High hardness		
Appearance	Available colors		
	Clear/transparent		
Forms	Sheet		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2760	MPa	ASTM D638
Tensile Strength	68.9	MPa	ASTM D638
Tensile Elongation (Break)	4.8	%	ASTM D638
Flexural Modulus	3280	MPa	ASTM D790
Flexural Strength	114	MPa	ASTM D790
Compressive Strength	124	MPa	ASTM D695
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		ASTM D542
Transmittance			ASTM D1003

-- ¹	92.0	%	ASTM D1003
--	92.0	%	ASTM D1003
Haze			ASTM D1003
-- ²	1.5	%	ASTM D1003
--	1.0	%	ASTM D1003
Yellowness Index			ASTM E313
-- ³	1.5	YI	ASTM E313
--	< 1.0	YI	ASTM E313
Additional Information	Nominal Value	Unit	Test Method
Sound Transmission Coefficient			ASTM E90
1.50 cm	32.0	dB	ASTM E90
2.00 cm	34.0	dB	ASTM E90
2.50 cm	36.0	dB	ASTM E90
Weight per Unit Area (1.50 cm)	3.66	lb/ft ²	
Resistance Against Stone Projectiles (15 mm thickness) : Pass (EN 1794-1)Impact-Windborne Debris in Hurricanes : Pass (ASTM E-1996/97)			

NOTE

1. Weathered 5 years AZ
2. Weathered 5 years AZ
3. Weathered 5 years AZ

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT