Gallonprene® GP410-7001

Thermoplastic Elastomer

Shenzhen Sungallon Rubber & Plastic Corporation Limited

Message:

Gallonprene® GP410-7001 is a thermoplastic elastomer (TPE) product. It can be processed by blow molding or injection molding and is available in Africa and the Middle East, Latin America or Asia Pacific. Gallonprene® GP410-7001 application areas include engineering/industrial accessories, consumer goods and handles.

Features include: Comply with REACH standard ROHS certification high gloss Halogen-free

General Information

| General information | | | | |
|--|---------------------------|----------|-------------|--|
| Features | Highlight | | | |
| | Sprayable | | | |
| | Halogen-free | | | |
| | | | | |
| Uses | overmolding | | | |
| | Blow molding applications | | | |
| | Soft handle | | | |
| | Toys | | | |
| | | | | |
| Agency Ratings | EC 1907/2006 (REACH) | | | |
| RoHS Compliance | RoHS compliance | | | |
| Appearance | White | | | |
| Processing Method | Blow molding | | | |
| | Injection molding | | | |
| | | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Specific Gravity | 0.958 | g/cm³ | ASTM D792 | |
| Melt Mass-Flow Rate (MFR) (200°C/5.0 kg) | 15 | g/10 min | ASTM D1238 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Durometer Hardness (Shore A, 23°C) | 70 | | ASTM D2240 | |
| Elastomers | Nominal Value | Unit | Test Method | |
| Tensile Strength ¹ (Break) | 7.50 | MPa | ASTM D412 | |
| Tensile Elongation ² (Break) | 600 | % | ASTM D412 | |
| Injection | Nominal Value | Unit | | |
| Rear Temperature | 155 - 175 | °C | | |
| Middle Temperature | 165 - 185 | °C | | |
| Front Temperature | 175 - 195 | °C | | |
| Processing (Melt) Temp | 140 - 160 | °C | | |
| | | | | |

| Mold Temperature | 30.0 - 60.0 | °C |
|------------------|-------------|----|
| Injection Rate | Fast | |

Injection instructions

Processing Temperature Limit: 220°CInjection Pressure: HighBack Pressure: 20 to 50%Overmolding Parameters:Rear Temperature: 165 to 185°CCenter Temperature: 175 to 195°CFront Temperature: 185 to 205°CMelt Temperature: 140 to 160°CMold Temperature: 30 to 60°CProcessing Temperature Limit: 220°CInjection Pressure: HighInjection Speed: HighBack Pressure: 20 to 50%

| NOTE | |
|------|------------|
| 1. | 500 mm/min |
| 2. | 500 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

