

Plaslube® PA6/6 N L

Polyamide 66
Techmer Engineered Solutions

Message:

Plaslube® PA6/6 N L is a Polyamide 66 (Nylon 66) product. It can be processed by injection molding and is available in North America. Characteristics include:
Flame Rated
Fast Molding Cycle
Low Viscosity
Lubricated

General Information			
Additive	Lubricant		
Features	Fast Molding Cycle		
	Low Viscosity		
	Lubricated		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.8	%	ASTM D955
Water Absorption (24 hr)	1.2	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	82.7	MPa	ASTM D638
Tensile Elongation (Yield)	80	%	ASTM D638
Flexural Modulus	2760	MPa	ASTM D790
Flexural Strength	138	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	221	°C	
1.8 MPa, Unannealed	71.1	°C	
CLTE - Flow	7.7E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+13	ohms · cm	ASTM D257
Dielectric Strength ¹	22	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method

Flame Rating (1.50 mm)	HB	UL 94
NOTE		
1.	Method A (Short-Time)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

