

POLYfill PPC B10075

Polypropylene Copolymer

Polykemi AB

Message:

Mineral reinforced

General Information			
Filler / Reinforcement	Mineral,75% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Density	2.25	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	17.0	MPa	ISO 527-2
Tensile Strain (Yield)	5.0	%	ISO 527-2
Flexural Modulus (23°C)	3000	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
--	150	°C	ISO 306/A50
--	87.0	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Glow Wire Ignition Temperature (2.00 mm)	750	°C	IEC 60695-2-13

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

