

MTEGRITY™ LLDPE LL204MM

Linear Low Density Polyethylene

M. Holland Company

Message:

Linear Low Density Polyethylene

Excellent Sealing Properties

Food Packaging

Stretch Wrap

General Information			
Features	Low density		
Uses	Stretch winding		
	Food packaging		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	0.918	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
1% secant, MD	193	MPa	ASTM D882
1% secant, TD	214	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Fracture	27.6	MPa	ASTM D882
TD: Fracture	21.4	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	700	%	ASTM D882
TD: Fracture	900	%	ASTM D882
Dart Drop Impact	110	g	ASTM D1709
Optical	Nominal Value	Unit	Test Method
Haze	13	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

