

BJB Polyurethane TC-812 A/B SLOW LIGHTCAST

Polyurethane

BJB Enterprises, Inc.

Message:

TC-812 A/B SLOW is a light weight filled, low viscosity, quick setting, easy to use casting material. A model or tool cast from TC-812 A/B SLOW will weigh 40% less than other unfilled urethane systems. Within 60 minutes after mixing and pouring, it is ready to be carved, sanded, filed, tapped, etc. Its characteristics make it ideal for lightweight backing of laminates and/or surface coats. Perfect for fast take offs, cores, engineering changes, temporary molds, patterns, models, prototypes, and bases for die molds.

General Information			
Filler / Reinforcement	Filler		
Features	Low Viscosity		
Uses	Laminates		
	Molds/Dies/Tools		
	Prototyping		
RoHS Compliance	RoHS Compliant		
Forms	Liquid		
Processing Method	Casting		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			ASTM D792
-- ¹	0.610	g/cm ³	
--	0.640	g/cm ³	
-- ²	0.650	g/cm ³	
Specific Volume	4340	cm ³ /g	
Gel Time	10.0 to 12.0	min	
Work Time ³ (25°C)	8.0 to 10.0	min	
Molding Shrinkage - Flow	0.30	%	ASTM D2566
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	60 to 65		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	17.8	MPa	ASTM D638
Flexural Modulus	1180	MPa	ASTM D790
Flexural Strength	18.8	MPa	ASTM D790
Compressive Strength	21.0	MPa	ASTM D695
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Part A	Mix Ratio by Weight: 100		
Part B	Mix Ratio by Weight: 100		

Shelf Life	26	wk	
Thermoset Mix Viscosity			ASTM D2393
25°C ⁴	750	cP	
25°C ⁵	875	cP	
25°C ⁶	650	cP	
Demold Time (25°C)	60 to 180	min	

NOTE

- | | |
|----|-------------|
| 1. | Part B |
| 2. | Part A |
| 3. | 1/2 lb mass |
| 4. | Mixed |
| 5. | Part B |
| 6. | Part A |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT