

# ELASTOSIL® E 47

Silicone

Wacker Chemie AG

## Message:

Silicone Rubber, RTV-1

Small Appliances, Household Appliances

Microwave Ovens, Household Appliances

Bonding for HTV, Plastics and Rubber Processing

Coating of Fabrics and Textiles, Technical Textiles

General Information			
Features	General Purpose		
Uses	Adhesives		
	Bonding		
	Sealants		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density			
--	1.00	g/cm <sup>3</sup>	DIN 51757
--	1.07	g/cm <sup>3</sup>	ISO 1183
Skin Forming Time <sup>1</sup> (23°C)	5.0 to 15.0	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	35		DIN 53505
Tensile Strength	4.50	MPa	DIN 53504
Tensile Elongation at Break	450	%	DIN 53504
Tear Strength	10.0	kN/m	
NOTE			
1.	50% R.H		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT