ISOTHANE® 3085A

Thermoplastic Polyurethane Elastomer (Polyether)

Great Eastern Resins Industrial Co Ltd (GRECO)

Message:

Tensile Elongation (Break)

ISOTHANE 3085A product is an 85A, polyether based thermoplastic Polyurethanes. It exhibits excellent hydrolytic resistance, fungus resistance and low temperature performance properties. It can be injection molded, blow molded, and extruded.

Suggested Applications:

Seals, Gaskets, Sheets, Film, Tube, Cable, Shoe Sole, Sporting Equipments and Mechanical Goods.

600

General Information					
Features	Fungus Resistant				
	Good Thermal Stability				
	Hydrolysis Resistant				
Uses	Cable Jacketing				
	Film				
	Footwear				
	Gaskets				
	Machine/Mechanical Parts				
	Seals				
	Sheet				
	Sporting Goods				
	Tubing				
	rubing				
Processing Method	Blow Molding				
	Extrusion				
	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.13	g/cm³	ASTM D792		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A)	85		ASTM D2240		
Mechanical	Nominal Value	Unit	Test Method		
Taber Abrasion Resistance (H-22 Wheel)	20.0	mg	ASTM D1044		
Elastomers	Nominal Value	Unit	Test Method		
Tensile Stress			ASTM D412		
50% Strain	4.50	MPa			
100% Strain	5.90	MPa			
300% Strain	12.0	MPa			
Tensile Strength (Yield)	37.0	MPa	ASTM D412		

%

ASTM D412

Tear Strength ¹	110	kN/m	ASTM D624
Compression Set			ASTM D395B
23°C, 22 hr	30	%	
70°C, 22 hr	35	%	
Extrusion	Nominal Value	Unit	
Drying Temperature	93.0	°C	
Cylinder Zone 1 Temp.	182 to 193	°C	
Cylinder Zone 2 Temp.	188 to 199	°C	
Cylinder Zone 3 Temp.	193 to 204	°C	
Adapter Temperature	193 to 204	°C	
Die Temperature	193 to 210	°C	
NOTE			
1.	Die C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

