

Topilene® R530

Polypropylene Homopolymer

Hyosung Corporation

Message:

Characteristics:

Transparency

FDA

DMF 21499

USP Class VI

SFDA

Applications:

IV bottle

| General Information | |
|---------------------|---------------------------------|
| Additive | High Slip |
| Features | High Clarity |
| | Homopolymer |
| Uses | Medical Devices |
| | Medical/Healthcare Applications |
| Agency Ratings | DMF 21499 |
| | FDA Unspecified Rating |
| | USP Class VI |

| Physical | Nominal Value | Unit | Test Method |
|---|---------------|----------|-------------|
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 6.0 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Flexural Modulus | 932 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Unnotched Izod Impact (23°C) | 59 | J/m | ASTM D256 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT