

RTP 2099 X 112329

Unspecified

RTP Company

Message:

ESD Protection - Extrusion Grade

General Information	
Features	ESD Protection
RoHS Compliance	Contact Manufacturer
Processing Method	Extrusion Extrusion

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm ³	ASTM D792
Moisture Content	< 0.020	%	

Extrusion	Nominal Value	Unit
Drying Temperature	65.0 to 75.0	°C
Drying Time	4.0 to 6.0	hr
Melt Temperature	210 to 230	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

