

InnoTuf® TP-4020

Polyurethane Thermoset Elastomer

Innovative Polymers, Inc.

Message:

TP-4020 is a stiff polyurethane formulated for room temperature hand-batch systems or vacuum casting systems. Excellent physical properties can be obtained without the utilization of mercury, MOCA, or TDI.

General Information			
Features	Good Stiffness		
RoHS Compliance	RoHS Compliant		
Appearance	Tan		
Processing Method	Vacuum Casting		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
Hardener	1.24	g/cm ³	
Cured	1.30	g/cm ³	
Base Resin	1.40	g/cm ³	
Molding Shrinkage - Flow	0.10 to 0.50	%	ASTM D2566
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	2760	MPa	ASTM D790
Flexural Strength	101	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	21	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	172	°C	ASTM D648
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
	Mix Ratio by Volume: 52		
Hardener	Mix Ratio by Weight: 46		
	Mix Ratio by Weight: 100		
Resin	Mix Ratio by Volume: 100		
Demold Time (66°C)	60	min	
Uncured Properties	Nominal Value	Unit	Test Method
Viscosity			
38°C ¹	0.50	Pa · s	

38°C ²	1.3	Pa·s	
38°C ³	7.8	Pa·s	
Curing Time ⁴	25	hr	
Gel Time	8.0 to 12	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	75 to 85		ASTM D2240
Tensile Strength	67.6	MPa	ASTM D638
Tensile Elongation at Break	2.0	%	ASTM D638
NOTE			
1.	Hardener		
2.	Mixed		
3.	Resin		
4.	1 hour at 150°F + 24 hours at 77°F		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT